

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**

**THIS PAGE BLANK (USPTO)**

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
25 May 2001 (25.05.2001)

PCT

(10) International Publication Number  
**WO 01/35898 A1**

(51) International Patent Classification<sup>7</sup>: A61J 1/00,  
B32B 27/08

(21) International Application Number: PCT/US00/27703

(22) International Filing Date: 6 October 2000 (06.10.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
09/439,826 12 November 1999 (12.11.1999) US

(71) Applicant: BAXTER INTERNATIONAL INC.  
[US/US]; Paula J.F. Kelly, One Baxter Parkway, DF3-3E,  
Deerfield, IL 60015 (US).

B-1170 Brussels (BE). DEWEZ, Jean-Luc; rue du  
Château 27, B-1470 Bousval (BE). HENAUT, Eric; 11,  
rue de la Samme, B-7181 Arquennes (BE). HOUWAERT,  
Vincent; 9, rue du Reposoir, B-7542 Mont-Saint-Aubert  
(BE).

(74) Agents: MATTENSON, Charles et al.; Baxter Healthcare  
Corporation, One Baxter Parkway, DF3-3E, Deerfield, IL  
60015 (US).

(81) Designated States (*national*): AU, BR, CA, CH, CN, CZ,  
DE, DK, ES, GB, HU, ID, IN, JP, KR, MX, PL, SE, SG,  
TR.

(84) Designated States (*regional*): European patent (AT, BE,  
CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC,  
NL, PT, SE).


(72) Inventors: PELUSO, Francesco; Verbindingslaan 70,  
B-3001 Heverlee (BE). ANDERS, Tranaeus; Rue du  
Mont Lassy 57, B-1380 Lasne (BE). FAICT, Dirk;  
Gravenstraat 1, B-9968 Assenede (BE). BALTEAU,  
Patric; Rue Louis Burtreau 69, B-5032 Bothey (BE).  
GOLLIER, Paul-André; 63, avenue du Cor de Chasse,

**Published:**

— With international search report.

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: MULTICHAMBER CONTAINERS FOR MEDICAL SOLUTIONS AND METHOD OF MANUFACTURING



(57) Abstract: A container (10) is provided comprising a body defined, at least in part, by a film, the body including at least one side seal, at least two chambers (12, 14) separated, at least in part, by a peelable seal, and the film including a sealant layer having a bimodal thermal behavior such that the side seal is a permanent seal and the peelable seal (16) can, at least in part, be separated.

WO 01/35898 A1

## SPECIFICATION

### TITLE

MULTICHAMBER CONTAINERS FOR MEDICAL SOLUTIONS AND METHOD OF MANUFACTURING.

5

### BACKGROUND OF THE INVENTION

The present invention relates generally to plastic films and containers made from same. More specifically, the present invention relates to containers for housing medical products and methods for manufacturing same.

10 It is known to house medical solutions in flexible containers constructed from plastic films. These containers can be used to house products such as parenteral, enteral, and dialysis solutions. Indeed, a great variety of different solutions can be housed and stored in such containers.

15 A number of issues are raised with respect to the containers for housing medical solutions, and the films that are used to construct such containers. These containers must be constructed so that they do not include harmful extractables that will leach out into the solution. This is especially important with respect to solutions such as parenteral solutions that are infused directly into the bloodstream of the patient.

20 Further, these containers must be able to stand up to certain rigors of use that other containers do not face due to environments in which they are used. Additionally, issues such as sterility and cleanliness, that may not be as critical with respect to containers used for non-infused solutions create manufacturing as well as product design issues for medical containers.

25 In fact, the products that are stored in the container themselves can create manufacturing, storage, and container design issues. There are a number of products that due to stability, compatibility, or other concerns must be stored in component parts, such as in separate containers, and admixed before use. This may be due to incompatibility of the products, for example, amino acids and dextrose solutions, or may be due to the fact that certain products must be maintained at different pHs from each other during sterilization or other processing, for example dextrose. Thus, it is known to provide  
30 multi-chambered containers. These containers include means by which the separate

chambers can be placed in fluid communication with each other allowing the solutions from each of the separate chambers to be intermixed within the container and then administered to the patient.

Multi-chambered containers are much more desirable than storing the components in separate containers and then mixing same together. In part because the process of opening and mixing separate containers can compromise the sterility of the system. Further, the step of opening and mixing separate container creates a labor intense process. Accordingly, to deal with the disadvantages of separate containers, it is known to provide containers having an interior including two or more chambers. One way to create such a container is with a heat seal dividing the interior into two chambers. Such containers are disclosed, for example, in U.S. Patent Nos.: 4,396,488; 4,770,295; 3,950,158; 4,000,996; and 4,226,330.

For example, it is also known to use frangible valves across the heat seal to allow for the selective communication and mixing of the components stored in the separate chambers. See, for example, U.S. Patent No. 4,396,488.

However, such structures - frangible valves - may not be desirable for a number of reasons including, inter alia, cost. An alternative to frangible valves is disclosed in U.S. Patent Nos.: 3,950,158; 4,000,996; and 4,226,330. In these patents, multiple chamber containers are disclosed with a line of weakness, such as a score line, which breaks upon the application of pressure.

It is also known to provide a selectively openable seal between two sheets of flexible thermoplastic material. U.S. Patent No. 4,770,295 provides a seal line that is resistant to unintentional opening forces, but opens upon the application of a specific force. The container includes two sheets that form the exterior of the container and an inner diaphragm sheet between the outer sheets. A selectably openable seal is disposed between one of the outer sheets and the diaphragm sheet. A permanent line of securement is preferably included between the exterior sheet and the diaphragm sheet extending substantially parallel to and coextensive with the openable seal line.

In addition, tear tabs or tear strips for plastic packaging are also known such as shown in U.S. Patent No. 2,991,000. These tear tabs can be used to provide access to the contents of the container. However, a disadvantage with these containers is that they

involve the use of relatively complicated seal structures. U.S. Patent No. 3,983,994 also discloses a seal broken by pulling upon tabs located outside the container.

Another issue that must be considered in constructing containers for the medical industry is that the solutions, and therefore the containers, often require sterilization after the manufacture of the container and/or introduction of the solution. Typically, the products are sterilized by steam sterilization or autoclaving. Autoclave sterilization can alter the thermal properties of the film used to form the container and the seal between the chambers of the container.

Of course, it is necessary in providing a multiple chamber container that the seal between the chambers is capable of withstanding external stresses encountered in normal handling, so that the seal is not prematurely opened. Such stresses include pressure that may be applied to one or more chambers from, for example, squeezing thereof incidental to packaging, or accidental dropping of the bag.

However, a difficulty in creating such a seal, using these types of materials is that the strength of the seal typically increases as a result of the heat applied during sterilization. As a result the seal may be too strong after the sterilization process making it difficult for the end user to separate or open the seal to combine the components within the chambers.

It is relevant to note that the end user of many of the medical solutions contemplated for use with the present invention is often the patient him or herself. This is particularly true in the case of the container being used to contain and administer solutions for peritoneal dialysis. Peritoneal dialysis is an alternative method to traditional hemodialysis by which a patient having end stage renal disease essentially treats him or herself by self-administering dialysis solutions a few times each day. However, patients undergoing dialysis tend to be elderly, often also diabetic, with poor eyesight and substantial weakness and diminished dexterity. Therefore, it is crucial that the force required to open the seal between chambers be carefully controlled to withstand normal handling and a certain amount of accidental jostling, yet not so great as to be difficult for such a patient to readily break when required to do so.

U.S. Patent No. 5,577,369 discloses a flexible container including a plurality of internal compartments separated by a seal. At least the seal region is constructed from

a film that comprises at least two layers, one of which is RF-responsive and the other layer, the inner layer, being non RF-responsive. The RF-responsive layer, in response to RF energy heats the non RF-responsive interior layer to form a peelable seal that is defined by a bonding between the non RF-responsive layers that define the interior of the container.

U.S. Patent No. 5,209,347 discloses an internal tear seal container having at least two chambers. A selectively openable seal line is provided connecting two sheets of material. The selectively openable seal line is resistant to unintentional opening but opens upon the application of a specific force.

10

### SUMMARY OF THE INVENTION

The present invention provides improved medical solution containers as well as methods for manufacturing same. The containers of the present invention include at least two chambers. The container is specifically designed for housing medical solutions although it can house other solutions and be used for other purposes.

15

To this end, in an embodiment, a container is provided by the present invention comprising a body defined, at least in part, by a film, the body including at least one permanent seal. The container includes at least two chambers separated, at least in part, by a peelable seal. The film includes a sealant layer exhibiting a bimodal thermal behavior such that the side seal is a permanent seal and the peelable seal can be opened.

20

In an embodiment, the sealant layer includes different polypropylene grades having different melting temperatures.

In an embodiment, the film includes an outer layer including polypropylene, a core layer including polyamide, and a sealant layer including polypropylene.

In an embodiment, the bimodal thermal behavior is such that a permanent seal is created at a temperature of at least 5°C greater than the peelable seal.

25

In an embodiment, the sealant layer includes polypropylene and linear low density polyethylene.

In an embodiment, the container includes a first area defined, in part, by a peelable seal. The first area is designed to separate upon an application of a sufficient fluid pressure. In a further embodiment, the first area is coupled to a tube.

30

In another embodiment of the present invention, a container is provided including at least one peripheral permanent seal and defining at least two chambers having therebetween a peelable seal. The container is constructed, at least in part, from a film comprising an external layer that defines an outer surface of the container; the external  
5 layer includes polypropylene polymers. The film includes a core layer; and a sealant layer that defines, at least in part, an interior surface of the container, the peelable seal, and the permanent seal. The sealant layer exhibiting a bimodal thermal property.

In an embodiment, the core layer includes polyamide.

In an embodiment, the sealant layer includes linear low density polyethylene.

10 In an embodiment, the bimodal thermal behavior of the sealant layer is such that a permanent seal is created at a temperature of at least 5°C greater than the temperature at which the peelable seal is created.

In an embodiment, the sealant layer includes styrene-ethylene-butylene-styrene (SEBS).

15 In an embodiment, the sealant layer includes: approximately 45% to about 80% by weight polypropylene (PP); approximately 5% to about 20% by weight linear low density polyethylene (LLDPE); approximately 0% to about 25% by weight SEBS.

In a further embodiment, the sealant layer includes: approximately 45 to 80% by weight polypropylene; approximately 5% to 15% by weight linear low density  
20 polyethylene, approximately 0% to about 25% by weight SEBS, and approximately 0 to about 20% by weight of EVA.

In an embodiment, the sealant layer includes at least two different grades of polypropylene that have different melting points.

In a still further embodiment of the present invention, a container is provided  
25 including at least one permanent peripheral seal and defining at least two chambers having therebetween a peelable seal. The container is constructed, at least in part, from a film comprising: an external layer that defines an outer surface of the container, the external layer including polypropylene; a core layer; and a sealant layer that defines, at least in part, an interior surface of the container, the peelable seal, and the permanent seal.  
30 The sealant layer having a bimodal thermal property and including polypropylene, linear low density polyethylene, SEBS, and EVA.



In yet another embodiment of the present invention, a container is provided including at least one permanent side seal and defining at least two chambers having therebetween a peelable seal. The container is constructed, at least in part, from a film comprising: an external layer that defines an outer surface of the container, the external layer including polypropylene; a core layer; and a sealant layer that defines, at least in part, an interior surface of the container, the peelable seal, and the permanent seal. The sealant layer having a bimodal thermal property and including polypropylene having at least two grades having a different melting point.

It is an advantage of the present invention to provide an improved medical container for housing solutions.

A further advantage of the present invention is to provide a new film for use in constructing flexible medical containers.

Another advantage of the present invention is to provide an improved seal for creating multi-compartmented medical containers.

Still further an advantage of the present invention is to provide an improved medical container for housing two solutions in separate compartments that can be mixed together, prior to use, in the container.

Further, an advantage of the present invention is to provide an improved method for manufacturing medical containers.

Furthermore, an advantage of the present invention is to provide an improved method for making a peelable seal.

These and other features of the present invention as well as advantages thereof are set forth in and or will be apparent from the following detailed description of the presently preferred embodiments and accompanying drawings.

#### BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 illustrates a perspective view of the front side of an embodiment of a multi-chambered container of the present invention.

Figure 2 illustrates a cross sectional view of an embodiment of the film of the present invention

Figure 3 provides a digital scanning calorimetry thermogram illustrating the seal strength versus sealing temperature of the sealant layer of an embodiment of the film of the present invention.

Figure 4 illustrates a cross sectional view of another embodiment of the film of the present invention.

Figures 5(a) and 5(b) respectively illustrate an embodiment of a method of manufacturing a peelable seal and a permanent seal using an embodiment of the film of the present invention.

Figure 6 illustrates graphically peel strength versus temperature of an embodiment of the seal layer of the present invention.

Figure 7 illustrates graphically peel strength versus temperature of an embodiment of the seal layer of the present invention.

Figure 8 illustrates graphically peel strength versus temperature of an embodiment of the seal layer of the present invention.

Figure 9 illustrates graphically peel strength versus temperature of an embodiment of the seal layer of the present invention.

Figure 10 illustrates another embodiment of the container of the present invention.

#### DETAILED DESCRIPTION OF THE PRESENTLY PREFERRED EMBODIMENTS

The present invention relates generally to containers for housing medical solutions. As noted previously, however, the container of the present invention can be used for housing other types of products.

Referring now to Figure 1, illustrated generally is an embodiment of a multi-chambered container 10 of the present invention. Although as illustrated the container includes two chambers 12 and 14, more than two chambers can be provided. The chambers 12 and 14 are designed for the separate storage of substances and/or solutions. A peelable seal 16 is provided between the chamber 12 and 14. Of course, if additional chambers are provided, additional peelable seals can be provided.

In the illustrated embodiment, the container 10 is formed from a flexible sheet of

plastic. The container 10 may be formed from two sheets of film that are heat sealed along their edges (11, 13, 15, and 17 respectively). However, the container 10 can also be formed from a web of film folded over and sealed along three sides. Pursuant to the present invention, the container is formed from a multi-layer film discussed below.

5 In the illustrated embodiment, two sheets of film are used. The sheets are sealed about the periphery of the container 10 at edges 11, 13, 15, and 17. A peelable seal 16 is provided between the sheets of film to form the chambers 12 and 14.

In a preferred embodiment that is illustrated in Fig. 1 at an end of the container a tubular port 22 is provided. The tubular port 22 provides communication with the  
10 interior of chamber 12, but could be located at any appropriate location on container 10. The port 22 can include a suitable membrane covering which can be pierced by, for example, a cannula or a spike of an administration set. This allows additional substances to be aseptically added to chamber 12 or, once seal 16 is opened, to the container 10.

In the illustrated embodiment, disposed at a bottom end of the container 10 are  
15 three tubular ports 23, 25, and 27 which communicate with the interior of chamber 14. These ports allow fluid to be added to the chamber 14, or, once seal 16 is opened, to container 10 or dispersed to a patient therefrom. The ports 23, 25, and 27 can also include a membrane (not shown) that is pierced by, for example, the cannula or spike of an administration act.

20 It will be appreciated that ports such as 22 and 23 for filling the container 10 are not a requirement of the invention. Depending on the method employed to manufacture the containers, fill ports may not be necessary at all. For example, if the containers are to be manufactured from a continuous roll of plastic film, the film could be folded lengthwise, a first permanent seal created, the first compartment filled with solution, then  
25 a peelable seal created, a second compartment filled, a permanent seal created, and so on.

Pursuant to the present invention, a novel peelable seal 16 is provided. The container 10 and thus the peelable seal 16 is provided by utilizing films that include a novel sealant layer. The sealant layer allows both a peelable and permanent seal to be created. Thus, the permanent side seals 11, 13, 15, and 17 as well as the peelable seal 16  
30 can be created from the same layer of film.

Referring to Figure 2, an embodiment of the film 30 of the present invention is illustrated. The film 30 is illustrated in cross-section and includes at least three layers 32, 34 and 36. Layer 36 defines an exterior of the container 10, layer 34 defines a core layer and layer 32 defines the sealant layer. In the illustrated embodiment, the layers are  
5 secured together by tie layers 38 and 40.

The sealant layer 32 provides a layer having bimodal thermal behavior. In an embodiment, the sealant layer 32 comprises a composition that is made from the same material but different grades of material. In this regard, in an embodiment, the sealant layer 32 is a blend of different polypropylene grades having different melting  
10 temperatures due to their tacticity differences, or high ethylene random copolymer content. For example, in an embodiment, high crystalline polypropylene polymers are used. High crystalline polypropylene polymers have a high melting temperature; preferably the melting temperature is above a 140°C. Additionally, these polymers have a narrow melting range.

15 Preferably, additionally the sealant layer 32 includes a more amorphous polypropylene with a melting temperature lower than 130°C. This lower melting point could, for example, be due to this second grade of polypropylene being more amorphous less crystalline in character than the first grade of polypropylene grade in layer 32.

20 Using such materials, a peelable seal 16 can be made by melting the two opposing sealant layers 32 of the container 10 together whenever a peelable seal is desired at a temperature of for example between approximately 125°C and 129°C. A permanent seal can be created by melting the two sealant layers 32 together at a temperature of above 135°C. Thus, the same sealant layer 32 can create both the permanent side seals and the  
25 peelable seals by merely forming each seal within a different temperature range. A variety of different sealing techniques can be used to make such seals including heat sealing, impulse sealing, and sonic sealing.

In this embodiment of the sealant layer 32, the peelable seal 16 is created due to a fusion of only the more amorphous low melting temperature polypropylene contained  
30 in the opposing sealant, side layer 32. Only these polymers participate in the resultant adhesion. By varying the composition of the sealant layer 32, one should be able to

determine the adhesion level in the preferable range.

Referring to Figure 3, a digital scanning calorimetry thermogram is illustrated. This thermogram demonstrates the bimodal behavior of materials of the present invention. The materials were measured by a commercial digital scanning calorimeter available from Mettler under the designation DSC 12E. In measuring the material, the material was submitted to a first heating cycle, from 30°C to 220°C at 20°C/min, cooled down to 30°C at 10°C/min, and finally the measurement was carried out in a third heating step from 30°C to 250°C at 20°C/min. The heat flow is measured by comparison with a reference.

The embodiment of the film illustrated in Figure 2 includes an outer layer 36 that comprises polypropylene. A tie layer 38 is located between the outer layer 36 and the core layer 34. The tie layer 38 may be polypropylene grafted maleic anhydride. The core layer 34 may be polyamide and preferably polyamide 6. This core layer 34 is then secured to the sealant layer 32 preferably utilizing another tie layer 40 of polypropylene grafted maleic anhydride.

Preferably, the outer layer 36 has a higher melting temperature than the internal layers of the film 30 in order to avoid adhesion during the sterilization process. This also prevents adhesion of the sealing die to the outer layer should heat seal dies be used to create the seals.

The core layer 34 of the film 30 should provide good mechanical and diffusion properties. The core layer 34 should maintain these properties even at temperatures up to 200 °C, which is much greater than the sealing temperatures.

Referring now to Figure 4, another embodiment of the film 41 is illustrated. In this embodiment, the sealant layer 42 comprises polypropylene and linear low density polyethylene. In a preferred embodiment, the layer 42 comprises approximately 70% by weight polypropylene (PP). Polypropylene is a semi-crystalline polyolefin with a melting point between 126°C and 170°C (depending on the crystallinity of the material). It is most desirable that the polypropylene has a continuous phase, therefore, in a preferred embodiment the concentration should be at least approximately 60% by weight.

The sealant layer 42 also preferably includes linear low density polyethylene. Preferably in an embodiment, the sealant layer 42 comprises approximately 10% linear

low density polyethylene (LLDPE) by weight dispersed in the polypropylene matrix. The linear low density polyethylene is a semi-crystalline polyolefin with a melting point between approximately 90° and 130°C. It could be used in a concentration ranging from between approximately 5 and 15% by weight.

5        Linear low density polyethylene in the sealant layer 42 plays two roles. It has a lower melting point than polypropylene and so it increases the bimodal thermal behavior of the blend. Also the highly amorphous character of linear low density polyethylene increases the mobility and compatibility of the dispersed phase, producing a better blend.

10        In an embodiment, the sealant layer also includes approximately 20% by weight styrene-ethylene-butylene-styrene (SEBS). SEBS is a triblock copolymer. In this regard, it comprises polystyrene block/ethylene-butylene copolymer block/polystyrene block. Ethylene-butylene is an elastomer. The complete triblock acts as a thermoplastic elastomer with a softening temperature at about 100°C. It should be the second dispersed phase, with concentrations between approximately 5 to about 20% by weight. The  
15        emulsion character of this triblock copolymer produces a low mobility even at temperatures above the softening point.

20        It should be noted in the above embodiment that ultra low density polyethylene (ULDPE) can be used in the same concentration as a replacement either in whole or in part for linear low density polyethylene and ethylene vinyl acetate could be added to improve scalability properties.

25        A principal of this embodiment of the peelable seal is that at low seal temperature (i.e., peel seal temperature) the sealant layer 42 behaves as a solid. Referring to Figures 5(a) and 5(b), the sealing of two sealant layers 42 and 42' together is illustrated. Specifically a peelable seal 43 and a permeant seal 45 are illustrated as being produced.

30        Referring specifically to Figure 5(a), when the sealant layers 42 and 42' are heated only the dispersed phase is liquid. Therefore, the adhesion occurs just at those points making bridges 50 and 52 between the seal 43 of two layers of film 42 and 42'. The peelable seal's 43 strength is proportional to the number of those bridges. So the peelable seal's 43 strength is governed not only by the composition of the sealant layer 42 and 42', but also by the microstructure and so by the thermal and mechanical history of the  
matured. Furthermore, because sterilization is conducted at a low temperature (e.g.

approximately 120°C) the sealant layer 42 and 42' are solid. there is no viscous flow during the sterilization process reducing both intermixing and formation of the sealing bead.

Referring to Figure 5(b), at higher temperatures, the sealant layers 42 and 42' each behave as viscous fluid leading to strong intermixing and formation of a sealing bead. This produces a permanent seal 45.

The sealant layer 42 provides a real bimodal system, with a plateau zone of peel sealability between approximately 110°C to about 125°C and a second plateau of permanent sealability. The linear low density polyethylene (highly amorphous) plays the role of a plasticizer and maybe a compatibilizer.

By way of example, a not limitation, examples of the present invention and testing thereof will now be given.

#### Example No. 1

In this example, the sealant layer comprised:  
approximately 45 to about 54% PP,  
approximately 18 to about 27% SEBS,  
approximately 9 to about 14% EVA,  
approximately 4.5 to about 9% Parafin oil,  
approximately 9.8% LLDPE, and  
approximately 2% ABPP.

Figure 6 illustrates graphically peel strength versus temperature for a sealant layer constructed pursuant to the above formulation. The seal was done on a thermal sealer with a pressure of 2MPa for a 3 second welding time. The seals were 200mm long and 4mm wide. The strength measurements were performed on an Instron tensile machine on 15mm wide strips cut perpendicular to the seal.

#### Example No. 2

In this example, the sealant layer comprised:  
65% PP co-ethylene random (4% ethylene), and  
35% syndiotactic PP.

Figure 7 illustrates graphically peel strength versus temperature for a sealant layer constructed pursuant to the above formulation. The seal was done on a thermal sealer

with a pressure of 2MPa for a 3 second welding time. The seals were 200mm long and 4mm wide. The strength measurements were performed on an Instron tensile machine on 15mm wide strips cut perpendicular to the seal.

Example No. 3

5 In this example, the sealant layer comprised:  
60% PP co-ethylene random,  
25% SEBS, and  
15% LLDPE.

10 Figure 8 illustrates graphically the seal strength. The seal was done on a thermal sealer with a pressure of 2MPa for a 3 second welding time. The seals were 200mm long and 4mm wide. The strength measurements were performed on an Instron tensile machine on 15mm wide strips cut perpendicular to the seal.

Example No. 4

15 In this example, the sealant layer comprised:  
60% PP,  
20% SEBS,  
10% EVA, and  
10% LLDPE.

20 Figure 9 illustrates graphically seal strength. The seal was done on a thermal sealer with a pressure of 2MPa for a 3 second welding time. The seals were 200mm long and 4mm wide. The strength measurements were performed on an Instron tensile machine on 15mm wide strips cut perpendicular to the seal.

The conclusions drawn from the data for the above four examples include:

- 1 All the tested formulations have peelable properties;
- 25 2. The addition of EVA increases the peelable value, i.e., the amount of force required to open the seal;
3. It appears that the addition of EVA decreases the strength of the permanent seal, apparently due to lower adhesion on the tie layer; and
4. Compounding LLDPE instead of dry blending has strong influence on the  
30 strength value.

Referring now to Figure 10, an embodiment of the present invention is illustrated.



The container 60 in the embodiment illustrated is provided having two chambers 62 and 64 that are separated by a peel seal 66. However more than two chambers can be provided. As illustrated, the container 60 includes a port 67 that allows fluid communication outside of the container 60.

5       The container 60 includes an interior area 68 that is in fluid communication with an interior 69 of the port 67. The interior area 68 is defined in part by a peelable seal 70. Although it is not necessary, the peelable seal 70 can have a peel strength, in a preferred embodiment that is greater than the peel strength of the peelable seal 66. In use the first peelable seal 66 is separated, this allows solutions in chamber 62 and 64 to be mixed.  
10   When further pressure is applied, peelable seal 70 will open and the mixed solution becomes available for infusion to the patient through the port.

It should be understood that various changes and modifications to the presently preferred embodiments described herein will be apparent to those skilled in the art. Such changes and modifications can be made without departing from the spirit and scope of  
15   the present invention and without diminishing its attendant advantages. It is therefore intended that such changes and modifications be covered by the appended claims.

WE CLAIM:

1. A container comprising:  
a body defined, at least in part, by a film, the body including at least one side seal;  
at least two chambers separated, at least in part, by a peelable seal; and  
5 the film including a sealant layer having a bimodal thermal behavior such that the  
side seal is a permanent seal and the peelable seal can, at least in part, be separated.
2. The container of Claim 1 wherein the sealant layer includes polypropylene  
and linear low density polyethylene.
- 10 3. The container of Claim 1 wherein the film includes:  
an outer layer including polypropylene;  
a core layer including polyamide; and  
a sealant layer including polypropylene.
4. The container of Claim 1 wherein the bimodal thermal behavior is such  
15 that a permanent seal is created at a temperature of at least 5°C greater than a temperature  
at which the peelable seal is created.
5. The container of Claim 1 wherein the sealant layer includes different  
polypropylene grades having different melting temperatures.
6. The container of Claim 1 wherein the sealant layer includes ethylene vinyl  
20 acetate.
7. The container of Claim 1 including a first area defined, in part, by a  
second peelable seal, the second peelable seal being designed to separate upon an  
application of a sufficient fluid pressure.

8. The container of Claim 1 including a port and an interior area in fluid communication with at least a portion of the port, the interior area being defined, at least in part, by a second peelable seal that segregates the interior area from at least one of the chambers.
- 5 9. The container of Claim 7 wherein the first area is coupled to a tube.
10. A container including at least one permanent side seal and defining at least two chambers having therebetween a peelable seal, the container is constructed, at least in part, from a film comprising:
- 10 an external layer that defines an outer surface of the container, the external layer including polypropylene;
- a core layer; and
- a sealant layer that defines, at least in part, an interior surface of the container, the peelable seal, and the permanent seal, the sealant layer having a bimodal thermal property and including polypropylene.
- 15 11. The container of Claim 10 wherein the core layer includes polyamide.
12. The container of Claim 10 wherein the sealant layer includes linear low density polyethylene.
13. The container of Claim 10 wherein the bimodal thermal behavior of the sealant layer is such that a permanent seal is created at a temperature of at least 5°C
- 20 greater than a temperature at which the peelable seal is created.
14. The container of Claim 10 wherein the sealant layer includes SEBS.
15. The container of Claim 10 wherein the sealant layer includes ethylene vinyl acetate.

16. The container of Claim 10 wherein the sealant layer includes:  
approximately 45% to about 80% by weight polypropylene;  
approximately 5% to about 20% by weight linear low density polyethylene;  
approximately 0% to about 25% by weight SEBS; and  
5 approximately 0% to about 15% by weight ethylene vinyl acetate.

17. The container of Claim 10 wherein the sealant layer includes at least two different grades of polypropylene having different melting points.

18. A container including at least one permanent side seal and defining at least two chambers having therebetween a peelable seal, the container is constructed, at least  
10 in part, from a film comprising:

an external layer that defines an outer surface of the container, the external layer including polypropylene;

a core layer; and

a sealant layer that defines, at least in part, an interior surface of the container, the  
15 peelable seal, and the permanent seal, the sealant layer having a bimodal thermal property and including polypropylene, linear low density polyethylene and SEBS.

19. The container of Claim 18 wherein the sealant layer includes EVA.

20. The container of Claim 18 including a first area defined, in part, by a second peelable seal that is located in juxtaposition to a side of the container, the second  
20 peelable seal being designed to separate upon an application of a sufficient fluid pressure.

21. The container of Claim 18 including a port and an interior area in fluid communication with at least a portion of the port, the interior area being defined, at least in part, by a second peelable seal that segregates the interior area from at least one of the  
25 chambers.

22. The container of Claim 18 wherein the first area is coupled to a tube.

23. The container of Claim 18 wherein the sealant layer includes at least 45% by weight polypropylene.

24. The container of Claim 18 wherein the sealant layer includes:  
approximately 45% to about 80% by weight polypropylene;  
5 approximately 5% to about 20% by weight linear low density polyethylene; and  
approximately 0% to about 25% by weight SEB; and  
approximately 0% to about 15% by weight EVA.

25. A container including at least one permanent side seal and defining at least two chamber, having therebetween a peelable seal the container is constructed, at least  
10 in part, from a film comprising:

an external layer that defines an outer surface of the container, the external layer including polypropylene,

a core layer, and

a sealant layer that defines, at least in part, an interior surface of the container, the  
15 peelable seal, and the permanent seal, the sealant layer having a bimodal thermal property and including at least two grades of polypropylene each having a different melting point.

26. The container of Claim 25 wherein the bimodal thermal behavior is such that a permanent seal is created at a temperature of at least 5°C greater than the temperatures at which the peelable seal is created.

20 27. The container of Claim 25 including a first area defined, in part, by a second peelable seal the second peelable seal designed to separate upon an application of a sufficient fluid pressure.

28. The container of Claim 25 including a port and an interior area in fluid  
25 communication with a portion of the port, the interior area being defined, at least in part, by a second peelable seal that segregates the interior area from at least one of the chambers.







FIG.3




FIG.5(a)




FIG.5(b)






FIG.6




FIG.7




FIG.8





FIG. 9



# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/27703

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 7 A61J1/00 B32B27/08

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 A61J B32B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 95 26177 A (FRESENIUS AG ;HEILMANN KLAUS (DE); KREISCHER THOMAS (DE); ZIMMERMA) 5 October 1995 (1995-10-05)  page 2, paragraph 4 -page 5, paragraph 1 page 7, paragraph 5; example 1	1,2,4, 10, 12-14, 18,23
A	---	25
X	WO 97 37628 A (BROOLING CATHRINE ;PHARMACIA & UPJOHN AB (SE); GUSTAFSSON BO (SE);) 16 October 1997 (1997-10-16)  claims 1,32 page 9, line 8 -page 10, line 32	1,4,5, 10,13, 14,17, 25,26
A	---	18
	--- -/--	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

\* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*Z\* document member of the same patent family

Date of the actual completion of the international search

6 February 2001

Date of mailing of the international search report

20/02/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Ibarrola Torres, O

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/27703

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 928 213 A (BARNEY WARD W ET AL) 27 July 1999 (1999-07-27) column 7, line 35 -column 8, line 55 column 9, line 12 -column 10, line 20 column 15, line 33-52; figures 3,5; table 1	1,4,10, 13,14
A	-----	18,25
X	US 4 961 495 A (YOSHIDA TAKAO ET AL) 9 October 1990 (1990-10-09) claims	1,2,4
A	-----	10,18,25
A	US 5 482 771 A (SHAH GAUTAM P) 9 January 1996 (1996-01-09) claims 1,11,12,22; figure 2 -----	3,11

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/27703

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9526177 A	05-10-1995	DE 4410876 A	05-10-1995
		BR 9505793 A	27-02-1996
		CA 2163022 A	05-10-1995
		DE 19536546 A	03-04-1997
		EP 0700280 A	13-03-1996
		JP 8511216 T	26-11-1996
		US 6017598 A	25-01-2000
WO 9737628 A	16-10-1997	AU 719057 B	04-05-2000
		AU 2418497 A	29-10-1997
		BG 62847 B	29-09-2000
		BG 102824 A	30-04-1999
		BR 9708630 A	03-08-1999
		CN 1218385 A	02-06-1999
		CZ 9803260 A	14-04-1999
		EP 0893982 A	03-02-1999
		HR 970195 A	30-04-1998
		HU 9901653 A	28-09-1999
		JP 2000504956 T	25-04-2000
		NO 984743 A	09-12-1998
		NZ 331981 A	28-05-1999
		PL 329293 A	15-03-1999
		SK 133798 A	10-03-1999
		US 6007529 A	28-12-1999
		ZA 9702965 A	14-08-1998
US 5928213 A	27-07-1999	US 5944709 A	31-08-1999
		AU 9674798 A	31-05-1999
		EP 1034006 A	13-09-2000
		WO 9924086 A	20-05-1999
		US 6117123 A	12-09-2000
		TW 384221 B	11-03-2000
		US 6165161 A	26-12-2000
		US 5910138 A	08-06-1999
		AU 721838 B	13-07-2000
		AU 2456497 A	05-12-1997
		BR 9708993 A	02-05-2000
		EP 0898466 A	03-03-1999
		JP 2000510728 T	22-08-2000
		NO 985266 A	13-01-1999
		WO 9742897 A	20-11-1997
US 4961495 A	09-10-1990	JP 2004671 A	09-01-1990
		JP 2675075 B	12-11-1997
		DE 68918162 D	20-10-1994
		DE 68918162 T	11-05-1995
		EP 0345774 A	13-12-1989
US 5482771 A	09-01-1996	AU 674873 B	16-01-1997
		AU 4737893 A	24-03-1994
		AU 695543 B	13-08-1998
		AU 7053796 A	16-01-1997
		BR 9303823 A	22-03-1994
		CA 2106258 A	19-03-1994
		CN 1084452 A	30-03-1994
		EP 0588667 A	23-03-1994
		JP 6198826 A	19-07-1994
		KR 9614027 B	11-10-1996

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/27703

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5482771 A		MX 9305734 A	30-06-1994
		NZ 248674 A	26-03-1996
		US 5543223 A	06-08-1996
		US 5910374 A	08-06-1999
		ZA 9306771 A	14-04-1994
<hr/>			